

# SPETEC PUR H100 HOT SHOT CARTRIDGE

WATER ACTIVATED SEMI-FLEXIBLE POLYURETHANE FOAM INJECTION RESIN.



## DESCRIPTION

SPETEC PUR H100 HOT SHOT CARTRIDGE is a one component, closed cell, hydrophobic, water reactive, solvent and phthalate free, low viscosity polyurethane injection resin for stabilization and water cut-off of large water leaks

## ADVANTAGES

- Single component cartridge.
- Good compression strengths.
- Rapid set time.
- No volatile solvents.
- Cures to rigid foam

## FIELD OF APPLICATION

- Water cut-off.
- Dams.
- Manholes.
- Storm pipe joints.
- Box culverts.
- Limited access areas

## APPLICATION

**Note:** the following are a few typical application descriptions. In case of other jobsite parameters, please contact our technical department.

### PRELIMINARY ANALYSIS

Hotshot cartridges are typically used to stop small leaks in walls or manholes. Holes are drilled all the way through the wall and the cartridge is used to pump grout into the soil on the other side. The grout reacts with the water in the soil to create a seal.

### PREPARATION OF THE PRODUCT

Read the technical and safety data sheets prior to commencement of the injection works. Vigorously shake the SPETEC PUR H100 HOT SHOT CARTRIDGE ACC accelerator before use and add the required quantity (2-10%) into the SPETEC PUR H100 HOT SHOT CARTRIDGE resin. Mix the accelerator homogeneously into the resin and protect against moisture and rain to prevent premature reaction. Only mix the amount of material that can be used the same day.

### COMPLIMENTARY PRODUCTS

If grout begins exiting the drill hole or any wide cracks and dripping outside of the wall, Oakum can be used to plug that grout leak.

### ADVICE / FOCAL POINTS

Avoid injecting when temperatures are below -4°F (-20°C). In extreme

cold conditions it is recommended to warm the resin and catalyst. Since SPETEC PUR H100 HOT SHOT CARTRIDGE is hydro active, liquid water should be present.

## TECHNICAL DATA

### APPEARANCE

**Physical Properties** - Uncured - (appearance brown liquid)

SPETEC PUR H100		
Viscosity at 77°F	(ASTM D4878-98)	±160cps
Flash Point	(ASTM D1310-86)	>302°F
Density	(ASTM D3505-96 [2000])	1.058 ± 0.005

**Physical Properties** - Uncured - (appearance yellow liquid)

H100 ACC		
Viscosity at 77°F	(ASTM D4878-98)	14cps
Flash Point	(ASTM D1310-86)	>302°F
Density	(ASTM D3505-96 [2000])	0.9 ± 0.003

**Physical Properties** - H100 + ACC Cured

SPETE PUR H100		
Hardness	ASTM D2240-00	69 Shore A
Compressive strength	ASTM D4219-93a	942psi
Tensile strength	ASTM D3574-03	290psi
Water Absorption	ASTM D2824	<1%
Density Confined	d ASTM D3574	55Lbs/cu.ft.
Corrosiveness	Non Corrosive	

## CONSUMPTION

Consumption has to be assessed on site and is influenced by the amount of water leaking, thickness of the concrete slab or wall, presence of voids in and around the concrete, etc.

### REACTION TIMES

Activation Times

H100 ACC	% ACC	CREAM	FULL RISE
77°F	15	15 sec.	40 sec.

## PACKAGING

SPETEC PUR H100 HOT SHOT CARTRIDGE Resin and Accelerator are packaged in a 10.5 ounce single cartridge.

## STORAGE AND SHELF LIFE

Store between 50° - 85° F (10° - 29° C).

## SAFETY PRECAUTIONS

Avoid contact with eyes and skin, always use personal protective equipment in compliance with local regulations. Read the relevant Safety Data Sheet before use. Safety Data Sheets are available on [www.alchemy-spetec.com](http://www.alchemy-spetec.com)

When in doubt contact Alchemy-Spetec Technical Service.

---

FOR INDUSTRIAL USE ONLY. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. READ MATERIAL SAFETY DATASHEET PRIOR TO EVERY USE.