



Certified Product Listing

For:

Drinking Water System Components - Health Effects

Company:

Alchemy Spetec
4508 Bibb Blvd
Suite B-5
Tucker, GA 30084, United States

Plant Location:

Tucker, GA, United States

Standards:

NSF/ANSI 61 Section 5 - 2017

Certificate:

Issued: 06/19/2018

Material/Product:

Spetec PUR F400- Polyurethane injection resin

Contact Temperature:

23 ± 2°C

Models:

Spetec PUR F400

Maximum surface area in contact with water shall not exceed more than 1% of the total surface area.



Product certified to NSF/ANSI 372 conforms to the requirements for "Lead Free" plumbing products as defined by California, Vermont, Maryland and Louisiana state laws and by section 1417 of the US SDWA.



Material Characteristics:

Minimum tank size (gallons): 40000

Maximum tank surface area/volume ratio (sq in/L): 1.7

Is additional coating required (e.g. top coat, primer, intermediate coat)? (Y/N): No

Total cure time and temperature: 24 hrs at 23 ± 2 °C

Final cure time: 24 hrs at 23 ± 2 °C

Mix ratio: 18:1:1

Is this paint/coating system intended to be applied to a pipe? (Y/N): No

Additional comments:

Maximum surface area in contact with water shall not exceed more than 1% of the total surface area.



Product certified to NSF/ANSI 372 conforms to the requirements for "Lead Free" plumbing products as defined by California, Vermont, Maryland and Louisiana state laws and by section 1417 of the US SDWA.